

## Technical Data Sheet

### Pro-design 90 GSM

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	90 +/- 3
Thickness	ISO 534	µm	99 +/- 3
Bulk	ISO 534		1,1
Moisture Content	ISO 287	%	4,4 +/- 0,6
Smoothness	ISO 5627	Bekk sec	130 +/- 20
Formation	Kajaani	Kajaani index	110
Whiteness	ISO 11475	CIE	168 +/- 3
Brightness D65	ISO 2470-2	%	112 +/- 1
Opacity	ISO 2471	%	Min 92
Stiffness MD	ISO 2493	mN	125 +/- 15
Stiffness CD	ISO 2493	mN	65 +/- 15

#### Production sites:

The production mills operate in compliance with the following standards



#### Special Attributes:



References:  
Product is made taking into account requirements of DIN EN 12281  
Product made from ECF Pulp  
ISO 45001 - Health & Safety