

Technical Data Sheet

160 GSM

| Parameters | Standard | Unit | Measurement |
|------------------|------------|------------------|-------------|
| Substance | ISO 536 | g/m ² | 160 +/- 3 |
| Thickness | ISO 534 | µm | 158 +/- 3 |
| Bulk | ISO 534 | | 0,99 |
| Moisture Content | ISO 287 | % | 4,7 +/- 0,6 |
| Smoothness | ISO 5627 | Bekk sec | 140 +/- 20 |
| Formation | Kajaani | Kajaani index | 110 |
| Whiteness | ISO 11475 | CIE | 168 +/- 3 |
| Brightness D65 | ISO 2470-2 | % | 112 +/- 1 |
| Opacity | ISO 2471 | % | Min 96 |
| Stiffness MD | ISO 2493 | mN | 455 +/- 20 |
| Stiffness CD | ISO 2493 | mN | 260 +/- 15 |

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:
Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp
ISO 45001 - Health & Safety