

Technical Data Sheet

200 GSM

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	200 +/- 5
Thickness	ISO 534	µm	196 +/- 3
Bulk	ISO 534		0,98
Moisture Content	ISO 287	%	4,6 +/- 0,6
Smoothness	ISO 5627	Bekk sec	135 +/- 20
Formation	Kajaani	Kajaani index	110
Whiteness	ISO 11475	CIE	168 +/-3
Brightness D65	ISO 2470-2	%	112 +/- 1
Opacity	ISO 2471	%	Min 98
Stiffness MD	ISO 2493	mN	700 +/- 30
Stiffness CD	ISO 2493	mN	400 +/- 20

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:
Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp
ISO 45001 - Health & Safety